



Prior to surface preparation and coatings



Duplex Fouling Release Red Silicone



Duplex Fouling Release Red Silicone

<b>Owner/Operator:</b>	<b>Crowley</b>
<b>Ship Yard/Applicator:</b>	<b>North Florida Shipyard, Jacksonville, FL</b>
<b>Vessel Type:</b>	<b>136' Tug Boat</b>
<b>Vessel Name:</b>	<b>Patriarch</b>
<b>New Construction / Maintenance:</b>	<b>Maintenance - full hull recoat, 8,000 sq/ft</b>
<b>Coating Application Date:</b>	<b>1/31/09 through 2/1/09</b>
<b>Coating In Service Date:</b>	<b>Not known</b>
<b>Coating System:</b>	<b>Abrasive blast</b> <b>1st coat - Sherwin Williams Seaguard 6100 (black) epoxy applied @ 6 mils dft</b> <b>2nd coat - Sherwin Williams Seaguard 6100 (red) epoxy applied @ 6 mils dft</b> <b>3rd coat - translucent silicone Duplex Tie Coat applied @ 6 mils dft</b> <b>4th coat - red silicone Duplex Surface Coat applied @ 6 mils dft</b>